



Designation: **A529/A529M – 19**

Standard Specification for High-Strength Carbon-Manganese Steel of Structural Quality¹

This standard is issued under the fixed designation A529/A529M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers carbon-manganese steel shapes, plates, and bars of structural quality for use in riveted, bolted, or welded construction of buildings and for general structural purposes.

1.2 Material under this specification is available in two grades:

Grade	Yield Strength, ksi [MPa]	Thickness
50 [345]	50 [345]	Plates to 1 in. [25 mm] thick to 15 in. [380 mm] wide Bars to 3½ in. [90 mm] Shapes with flange or leg thickness to 1½ in. [40 mm] inclusive
55 [380]	55 [380]	Plates to 1 in. [25 mm] thick to 15 in. [380 mm] wide Bars to 3 in. [75 mm] Shapes with flange or leg thickness to 1½ in. [40 mm] inclusive

1.3 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification **A6/A6M** for information on weldability.

1.4 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.02** on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved May 1, 2019. Published May 2019. Originally approved in 1964. Last previous edition approved in 2014 as A529/A529M – 14. DOI: 10.1520/A0529_A0529M-19.

2. Referenced Documents

2.1 *ASTM Standards:*²

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification **A6/A6M**, for the ordered material, unless a conflict exists in which case this specification shall prevail.

4. Materials and Manufacture

4.1 The steel shall be killed, and such shall be confirmed by a statement of *killed steel* on the test report or by a report on the presence of a sufficient quantity of a strong deoxidizing element, such as silicon at 0.10 % or higher, or aluminum at 0.015 % or higher.

5. Chemical Composition

5.1 *Heat Analysis:*

5.1.1 The heat analysis shall conform to the requirements prescribed in **Table 1** and be reported in accordance with relevant sections of Specification **A6/A6M**.

5.2 *Product Analysis:*

5.2.1 The steel shall conform on product analysis to the requirements of **Table 1**, subject to the product analysis tolerances in Specification **A6/A6M**.

6. Tension Test

6.1 The material as represented by the test specimen shall conform to the requirements as to the tensile properties prescribed in **Table 2**.

7. Keywords

7.1 bars; bolted construction; carbon; frames; metal building systems; plates; riveted construction; shapes; steel; structural steel; trusses; welded construction

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements (Heat Analysis)

NOTE 1—A maximum of 1.50 % manganese is permissible, with an associated reduction of the carbon maximum of 0.01 percentage point for each 0.05 percentage point increase in manganese.

Element	Composition, %
	Grades 50 [345] and 55 [380]
Carbon, max	0.27
Manganese, max	1.35
Phosphorus, max	0.04
Sulfur, max	0.05
Silicon, max	0.40
Copper, min, when copper is specified	0.20

TABLE 2 Tensile Requirements^A

	Grade 50 [345]		Grade 55 [380]	
	ksi	[MPa]	ksi	[MPa]
Tensile strength, min	65	[450]	70	[485]
Tensile strength, max	100	[690]	100	[690]
Yield strength, min	50	[345]	55	[380]
Elongation in 8 in. [200 mm], min, %	18		17	
Elongation in 2 in. [50 mm], min, %	21		20	

^A See the Orientation subsection in the Tension Tests section of Specification **A6/A6M**.

SUPPLEMENTARY REQUIREMENTS

Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A6/A6M**. Those that are considered suitable for use with this specification are listed by title:

S5. Charpy V-Notch Impact Test.

ADDITIONAL SUPPLEMENTARY REQUIREMENTS

In addition, the following optional supplementary requirements are also suitable for use with this specification.

S32. Single Heat Bundles

S32.1 Bundles containing shapes or bars shall be from a single heat of steel.

S78. Maximum Carbon Equivalent

S78.1 This material shall be supplied with a maximum carbon equivalent value of 0.55 % or to a lower value specified in the purchase documents. This value will be based on heat analysis. The required chemical analysis as well as the carbon equivalent shall be reported.

S78.2 The carbon equivalent shall be calculated using the following formula:

$$CE = C + (Mn + Si)/6 + (Cu + Ni)/15 + (Cr + Mo + V + Cb)/5$$

(Note: Columbium (Cb) and niobium (Nb) are interchangeable names for the same element.)

S79. Maximum Tensile Strength

S79.1 The maximum tensile strength shall be 90 ksi [620 MPa].

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A529/A529M – 14) that may impact the use of this standard. (Approved May 1, 2019.)

- (1) Revised wording of 4.1 to be consistent with other ASTM standards. (2) Added reporting statement to 5.1.1 and deleted 5.1.2 due to redundancy of requirements with Specification A6/A6M.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>